10/516586

#4

DESCRIPTION

ADSORBENT AND ADSORBER CAPABLE OF WHOLE BLOOD TREATMENT FOR

ADSORBING LOW-DENSITY LIPOPROTEIN AND FIBRINOGEN

5   Technical Field

The present invention relates to an adsorbent for

adsorbing low-density lipoproteins and fibrinogen present in

a body fluid to decrease the concentrations thereof in the

body fluid. Also, the present invention relates to a method

10   for removing low-density lipoproteins and fibrinogen from a

body fluid by adsorption on the adsorbent. Furthermore, the

present invention relates to an adsorber using the adsorbent

for low-density lipoproteins and fibrinogen in a body fluid.

Particularly, the present invention relates to an adsorbent

15   capable of whole blood treatment.

Background Art

In recent years, patients affected by arteriosclerosis

have increased in number with westernization of eating

habits and aging. It is well known that low-density

20   lipoproteins (LDL) and very low-density lipoproteins (VLDL)

are rich in cholesterol and thus cause arteriosclerosis. It

is also the fact that arteriosclerosis highly develops in

patients with hyperlipemia or hypercholesterolemia. On the

other hand, high-density lipoproteins (HDL) are known as a

25   retardation factor against arteriosclerosis.

Although therapies for these diseases include a dietary therapy and a drug therapy, a therapy applied to a patient who cannot be effectively treated by these therapies comprises extracorporeally removing low-density lipoproteins

5   from the blood by adsorption. In particular, a therapy of perfusing the blood plasma separated from the blood through an adsorber filled with an adsorbent comprising cellulose beads with immobilized dextran sulfate to remove the low-density lipoproteins is widely used with a high curative

10 effect.

On the other hand, it has been reported that a fibrinogen concentration is correlated with the incidence of coronary artery diseases and cerebral apoplexy (W. B. Kannel et al., The Journal of the American Medical Association, Vol.

15 258, pp. 1183-1186, 1987). In order to prevent the occurrence of these diseases related to arteriosclerosis, it is desired to decrease the fibrinogen concentration as well as the concentration of low-density lipoproteins.

In particular, arteriosclerosis causing the occlusion

20 of a peripheral blood vessel is referred to as "arteriosclerosis obliterans". In this disease, the peripheral blood vessel is narrowed or occluded to worsen the circulation of peripheral blood, thereby causing symptoms such as coldness in the limbs, numbness,

25 intermittent claudication, a pain at rest, an ulcer,

mortification, and the like, leading to limb amputation. It has been also reported that a patient with the arteriosclerosis obliterans having such lesions in the peripheral blood vessel has a higher fibrinogen

5   concentration than that of a healthy adult (P. Poredos et al., Angiology, Vol. 47, No. 3, pp. 253-259, 1996). In treatment of the arteriosclerosis obliterans, therefore, it is also desired to decrease the fibrinogen concentration as well as the concentration of low-density lipoproteins.

10   As described above, a therapy desired for a patient with arteriosclerosis, particularly arteriosclerosis obliterans, comprises decreasing the concentrations of low-density lipoproteins and fibrinogen in blood. The above-described therapy of removing the low-density lipoproteins

15   from blood plasma by adsorption on the adsorbent comprising cellulose beads with immobilized dextran sulfate is excellent in adsorption of the low-density lipoproteins, but the therapy is not necessarily sufficient for decreasing the fibrinogen concentration. In some cases, double filtration

20   plasmapheresis is applied. In this method, the plasma separated by a plasma separator is introduced into a plasma filter membrane to remove an unfiltered substance, i.e., a substance larger than the pore diameter of the membrane, together with water. This method can securely remove low-

25   density lipoproteins and fibrinogen, but it is

disadvantageous in that the filtration system used requires electrolytic transfusion (fluid replacement), and even if a complicated operation such as temperature control, recirculation, or the like is performed, selectivity for a

5   substance to be removed is lower than that of adsorption, thereby removing useful substances other than low-density lipoproteins and fibrinogen, for example, albumin, immunoglobulin such as IgG, HDL-cholesterol, and the like (Yoshie Konno, et al., Japanese Journal of Apheresis, Vo. 22,

10   No. 1, pp. 44-50, 2003). Furthermore, it has been reported that a therapy referred to as a "heparin precipitation method" has been developed for removing low-density lipoproteins and fibrinogen. However, this method comprises a complicated operation and is not popularized as a general

15   therapy.

      Also, it is known that fibrinogen and low-density lipoproteins can be removed with an adsorbent comprising a cross-linked porous material containing a compound in its surfaces, the compound having a hydrophobic structure and an

20   anionic functional group (Japanese Unexamined Patent Application Publication No. 7-136256). Although the adsorbent has excellent adsorption ability for fibrinogen, the adsorption ability for low-density lipoproteins is not sufficient. In order to exhibit the clinically sufficient

25   adsorption ability of the adsorbent, a large amount of the

adsorbent must be used. Therefore, the amount of the blood taken out from a body in a therapy is increased to increase the probability of occurrence of a blood pressure drop in the therapy. This document also discloses a preferred

5 method for using the adsorbent in which plasma is separated from blood by a plasma separator and then treated from the viewpoint of influences on blood cell components such as platelets.

Therefore, the conventional methods for decreasing the

10 low-density lipoproteins and fibrinogen are disadvantageous in that the methods comprise complicated operations due to a plasma separation system and have low performance, and useful substances are also removed. On the other hand, a system for direct whole blood treatment without plasma

15 separation from blood has recently attracted attention as an extracorporeal circulation therapy using an adsorbent in view of simplicity of operations and shortening of the therapy time. The direct whole blood treatment system does not require plasma separation using a plasma separator or

20 the like, and is capable of direct treatment of the blood anticoagulated with an anticoagulant. Therefore, the circuit is very simple, and the target substance can be effectively adsorbed within a short time. Consequently, a decrease in burden to a patient and medical staff is

25 expected.

However, the direct whole blood treatment system is required to decrease the interaction between the adsorbent and blood cells and decrease the influence on the blood cell components as much as possible. In the direct whole blood treatment, it is most important to inhibit the activation of leukocytes and platelets as much as possible. When the activation is low, a loss of these blood cells can be prevented. Particularly, when a blood vessel is damaged, the platelets adhere to the damaged site, and a fibrinogen receptor is expressed on the surface to form thrombus due to cross-linking of the platelets with fibrinogen. The thrombus possibly covers the damaged site to prevent a blood leakage. Therefore, the technique for adsorbing fibrinogen by whole blood treatment is considered very difficult. With respect to the above-described adsorbent comprising a cross-linked porous material containing a compound in its surfaces, the compound having a hydrophobic structure and an anionic functional group, there is no concrete study of a method of direct whole blood treatment, and a plasma treatment system is considered preferable (Japanese Unexamined Patent Application Publication No. 7-136256).

As described above, there has been no conventional method for effectively removing low-density lipoproteins and fibrinogen by a very simple operation of whole blood treatment without plasma separation and a loss of other

useful substances. Therefore, the development of such a method has been demanded.

Disclosure of the Invention

In order to solve the above problems, the present
5 invention provides an adsorbent for efficiently adsorbing low-density lipoproteins and fibrinogen from a body fluid, particularly whole blood, to decrease the concentrations of the low-density lipoproteins and fibrinogen in the body fluid while minimizing a loss of useful substances such as
10 albumin and HDL. The present invention also provides a method for adsorbing low-density lipoproteins and fibrinogen in a body fluid using the adsorbent. The present invention further provides an adsorber comprising the adsorbent for adsorbing low-density lipoproteins and fibrinogen in a body
15 fluid. Particularly, the present invention provides an adsorbent and adsorber capable of minimizing a loss of blood cells and safely treating whole blood.

The inventors carried out intensive research of an adsorbent capable of minimizing a loss of useful substances
20 such as albumin and HDL and effectively adsorbing low-density lipoproteins and fibrinogen by whole blood treatment. As a result, the inventors found an adsorbent comprising a tryptophan derivative and a polyanionic compound which are immobilized on a water-insoluble porous carrier, wherein a
25 predetermined amount of the polyanionic compound is

immobilized, and the molar ratio of the amount of the immobilized tryptophan to the amount of the immobilized polyanionic compound is in a specified range. Also, inventors found that the adsorbent is capable of safe whole

5   blood treatment for effectively adsorbing low-density lipoproteins and fibrinogen in a body fluid while minimizing a loss of blood cells. This finding resulted in the achievement of the present invention.

In a first aspect of the present invention, an

10   adsorbent capable of whole blood treatment for adsorbing low-density lipoproteins and fibrinogen comprises a tryptophan derivative and a polyanionic compound which are immobilized on a water-insoluble porous carrier, wherein the amount of the immobilized polyanionic compound is 0.10 μmol

15   to 1.5 μmol per milliliter of wet volume of the adsorbent, and the molar ratio of the amount of the immobilized tryptophan derivative to the amount of the immobilized polyanionic compound per milliliter of wet volume of the adsorbent is 1 to 70. In a second aspect of the present

20   invention, a method for adsorbing low-density lipoproteins and fibrinogen comprises bringing the adsorbent into contact with a body fluid containing the low-density lipoproteins and fibrinogen. In a third aspect of the present invention, an adsorber capable of whole blood treatment for absorbing

25   low-density lipoproteins and fibrinogen comprises a

container having a fluid inlet and outlet and a means for
preventing an outflow of the adsorbent to the outside, the
container being filled with the adsorbent for low-density
lipoproteins and fibrinogen.

5   In the present invention, the term "body fluid" means
blood or plasma.

       In the present invention, the term "polyanionic
compound" means a compound having a plurality of anionic
functional groups in its molecule. In the present invention,

10   examples of the anionic functional groups include functional
groups negatively charged at neutral pH, such as a carboxyl
group, a sulfonate group, a sulfate group, and a phosphate
group. Among these functional groups, from the viewpoint of
adsorption ability, a carboxyl group, a sulfonate group, and

15   a sulfate group are preferred. In view of highest
adsorption ability, a sulfate group is particularly
preferred.

       Representative examples of the polyanionic compound
include synthetic polyanionic compounds such as polyacrylic

20   acid, polyvinylsulfonic acid, polystyrenesulfonic acid,
polyglutamic acid, polyasparaginic acid, polymethacrylic
acid, polyphosphoric acid, and styrene-maleic acid
copolymers; synthetic acid polysaccharides such as dextran
sulfate and carboxymethyl cellulose; acid tissue-derived

25   acid mucopolysaccharides having sulfate groups, such as

chondroitin sulfate, dermantan sulfate, and keratan sulfate; acid mucopolysaccharides having N-sulfonate groups or sulfate groups, such as heparin and heparan sulfate; tissue-derived polysaccharides having anionic functional groups,

5 such as chondroitin and phosphomannan; and tissue-derived nucleic acids such as deoxyribonucleic acid and ribonucleic acid. However, the polyanionic compound is not limited to these representative examples.

Among these representative compounds, it is practical

10 to use synthetic compounds rather than directly using tissue-derived compounds because a high-purity substance can be obtained at low cost, and the amount of the anionic functional groups introduced can be controlled. From these viewpoints, synthetic polyanionic compounds such as

15 polyacrylic acid, polyvinylsulfuric acid, polyvinylsulfonic acid, polystyrenesulfonic acid, polyglutamic acid, polyasparaginic acid, polymethacrylic acid, polyphosphoric acid, and styrene-maleic acid copolymers; and synthetic acid polysaccharides such as dextran sulfate and carboxymethyl

20 cellulose are preferably used. In particular, from the viewpoint of low cost, polyacrylic acid, polystyrenesulfonic acid, and dextran sulfate are more preferred, and dextran sulfate is most preferred from the viewpoint of safety.

The molecular weight of the polyanionic compound is

25 preferably 1000 or more, and more preferably 3000 or more in

view of affinity for the low-density lipoproteins and the
fibrinogen adsorbing ability in combination with tryptophan.
Although the upper limit of the molecular weight of the
polyanionic compound is not particularly limited, the upper

5   limit is preferably 1,000,000 or less from the practical
viewpoint.

In the present invention, any one of various methods
for immobilizing the polyanionic compound to the water-
insoluble porous carrier may be used. Representative

10   examples of the method include (1) a grafting method using
radiation or electron beams for covalently bonding the
polyanionic compound to the surfaces of the water-insoluble
porous carrier, and (2) a chemical method of covalently
bonding the polyanionic compound through the functional

15   groups of the water-soluble porous carrier.

In the present invention, in view of the structure of
the adsorbent in which the polyanionic compound and the
tryptophan derivative are immobilized, the chemical method
of covalently bonding the polyanionic compound through the

20   functional groups is simpler and preferred because the
tryptophan derivative can be immobilized by the same method.

In the present invention, examples of the tryptophan
derivative include tryptophan, tryptophan esters such as
tryptophan ethyl ester and tryptophan methyl ester, and

25   compounds having indole rings and structures similar to

tryptophan, such as tryptamine and tryptophanol. The tryptophan derivative may be an L-isomer, a D-isomer, a DL-isomer, or a mixture thereof. Alternatively, a mixture of at least two tryptophan derivatives may be used. Among

5 these tryptophan derivatives, tryptophan is preferred from the viewpoint of safety, and L-tryptophan is most preferable in practical use because safety data is abundant, and tryptophan is a natural amino acid, most inexpensive, and readily available.

10 In the present invention, as the method for immobilizing the tryptophan derivative, the chemical method of covalently boding the tryptophan derivative through the functional groups of the water-insoluble porous carrier is preferably used.

15 In the present invention, the amount of the immobilized polyanionic compound must be 0.10 μmol to 1.5 μmol per milliliter of wet volume of the adsorbent, and the molar ratio of the amount of the immobilized tryptophan derivative to the amount of the immobilized polyanionic compound must

20 be 1 to 70.

In the present invention, the molar ratio (TR/PA ratio) of the amount of the immobilized tryptophan derivative to the amount of the immobilized polyanionic compound is calculated according to the following equation:

25 TR/PA ratio = molar number of the immobilized

tryptophan derivative per milliliter of wet volume of the adsorbent/molar number of the immobilized polyanionic compound per milliliter of wet volume of the adsorbent.

The inventors carried out intensive study on the amount of the immobilized polyanionic compound, the amount of the immobilized tryptophan derivative, low-density lipoproteins and fibrinogen, and blood cell passing property in direct whole blood treatment. As a result, it was surprisingly found that when the amount of the immobilized polyanionic compound is controlled to 0.10 μmol to 1.5 μmol per milliliter of wet volume of the adsorbent, and the molar ratio TR/PA is controlled to 1 to 70, high adsorption ability is exhibited for the low-density lipoproteins and fibrinogen, and passing property to leukocytes and platelets is excellent.

In the present invention, the amount of the immobilized polyanionic compound is 0.10 μmol to 1.5 μmol per milliliter (wet volume) of the adsorbent. With the amount of less than 0.10 μmol, the passing property to leukocytes and platelets is low to decrease the number of the leukocytes in the pooled blood in whole blood perfusion. With the amount of over 1.5 μmol, the fibrinogen adsorbing ability is less exhibited even when the tryptophan derivative is immobilized. In view of high blood cell passing property and high adsorption ability, the amount of the immobilized

polyanionic compound is preferably 0.12 μmol to 1.0 μmol, and more preferably 0.15 μmol to 0.50 μmol.

In the present invention, the molar ratio (TR/PA ratio) of the amount of the immobilized tryptophan derivative to the amount of the immobilized polyanionic compound is 1 to 70. With the TR/PA ratio of less than 1, the fibrinogen adsorbing ability of the tryptophan derivative is less exhibited. Conversely, with the TR/PA ratio over 70, the passing property to leukocytes and platelets gradually worsens to decrease the number of the leukocytes in the pooled blood in whole blood perfusion. In view of high blood cell passing property and high adsorption ability, the molar ratio is preferably 5 to 60, and more preferably 10 to 50.

In the present invention, the wet volume of the adsorbent is determined as follows: The adsorbent is immersed in water and transferred as slurry into a measuring container such as a measuring cylinder, and the adsorbent slurry is spontaneously settled in the measuring container. Then, a rubber mat is placed for preventing breakage of the measuring container, and the measuring container is gently dropped about 5 to 10 times onto the mat from a height of about 5 to 10 cm in the vertical direction (so that the settled adsorbent does not extremely rise) to apply vibration to the adsorbent. After the measuring container

is allowed to stand for 15 minutes or more, the volume of
the adsorbent settled is measured. The operation of
vibration and standing is repeated, and the volume of the
adsorbent settled is measured as the wet volume when the
5   volume of the adsorbent settled is not changed.

In the present invention, examples of the method for
measuring the amount of the immobilized polyanionic compound
include a method of determining the content of an element in
the polyanionic compound in the adsorbent (for example, when
10   dextran sulfate is the polyanionic compound, the sulfur
content in the adsorbent is determined), and a method of
measuring a decrease in amount of a pigment in a pigment
solution in contact with the adsorbent, the pigment having
the property of bonding to the polyanionic compound. Among
15   these methods, the method using the pigment solution is
capable of simply and precisely measuring the amount of the
immobilized polyanionic compound. The method will be
described in detail below in EXAMPLE 1. When the
polyanionic compound is dextran sulfate or polyacrylic acid,
20   the amount of the immobilized compound can be simply
measured from the amount of the toluidine blue adsorbed on
the adsorbent in contact with a toluidine blue solution
because the compound has the property of bonding to the
toluidine blue.

25   In the present invention, the amount of the immobilized

tryptophan derivative can be determined by using the

property that a color is generated when an aldehyde such as

p-dimethylbenzaldehyde is condensed with the indole ring in

the molecule of the tryptophan derivative under a strong

5   acid condition (Amino Acid Fermentation (second volume)

edited by Koichi Yamada, pp. 43-45, Kyoritsu Shupppan, 1972).

The amount of the immobilized tryptophan derivative can also

be determined by a method using the property that

fluorescent light with a peak at about 350 nm is emitted

10   when the indole ring in the molecule of the tryptophan

derivative is excited with light at about 280 nm. When the

carrier comprises a compound not containing nitrogen, the

amount can be measured by determining the nitrogen content

in the adsorbent, as will be descried in detail below in the

15   method of EXAMPLE 1.

In the present invention, the water-insoluble porous

carrier is water-insoluble at normal temperature and normal

pressure, and has fine holes of an appropriate size, i.e., a

porous structure. As the shape of the water-insoluble

20   porous carrier, any one of a spherical shape, a granular

shape, a flat membrane, a fibrous shape, a hollow fiber, and

the like may be effectively used. However, a spherical

shape or a granular shape is preferably used from the

viewpoint of ease of handling.

25   When the water-insoluble porous carrier has a spherical

shape or granular shape, the average particle size of the
carrier is preferably as large as possible in view of the
point that the adsorbent of the present invention is capable
of whole blood treatment. However, in view of adsorption

5   efficiency, the average particle size is preferably as small
as possible. In the present invention, in order to permit
the whole blood treatment and the exhibition of high
adsorption efficiency, the average particle size of the
adsorbent is preferably 100 μm to 1000 μm. Also, from the

10   viewpoint that high blood cell passing property and
adsorption efficiency can be exhibited, the average particle
size of the adsorbent is more preferably 200 μm to 800 μm,
and most preferably 400 μm to 600 μm.

The water-insoluble porous carrier preferably has a

15   molecular weight exclusion limit of 5×10^5 or more for
globular proteins. As described in a book (Size Exclusion
Chromatography, written by Sadao Mori, Kyoritsu Shuppan),
the molecule weight exclusion limit means the molecular
weight of a molecule having the smallest molecular weight

20   among the molecules not entering in fine pores (excluded)
when a sample having various molecular weights is flowed in
size exclusion chromatography. When the molecular weight
exclusion limit for globular proteins is less than 5×10^5,
it is not practical because of the low adsorption ability

25   for fibrinogen and low-density lipoproteins. When the

molecular weight exclusion limit for globular proteins is over 1×10^8, the pore size is excessively large to decrease the surface area contributing to adsorption, thereby decreasing the adsorption ability for fibrinogen and low-

5 density lipoproteins. In the present invention, therefore, the molecular weight exclusion limit of the water-soluble porous carrier for globular proteins is preferably 5×10^5 to 1×10^8, and more preferably 1×10^6 to 1×10^8, and most preferably 2×10^6 to 1×10^8 from the viewpoint of

10 exhibition of adsorption ability.

In the present invention, the water-insoluble porous carrier preferably has functional groups usable for bonding for immobilizing the polyanionic compound and the tryptophan derivative. Representative examples of the functional

15 groups include an amino group, an amide group, a carboxyl group, an acid anhydride group, a succinimide group, a hydroxyl group, a thiol group, an aldehyde group, a halogen group, an epoxy group, a silanol group, and a tresyl group. However, the functional groups are not limited to these

20 groups. The water-insoluble porous carrier may be activated by a method, for example, a halogenation-cyanidation method, an epichlorohydrin method, a bisepoxide method, or a bromoacetyl bromide method. Among these methods, the epichlorohydrin method is most preferably used from the

25 viewpoint of practical use and safety.

In the present invention, it is undesirable that the water-insoluble porous carrier is excessively soft or easily broken. When consolidation occurs during flowing of a body fluid, a sufficient flow rate of the body fluid cannot be

5 obtained to extend the treatment time and fail to continue the treatment. Therefore, in order to prevent the consolidation of the adsorbent, the adsorbent preferably has sufficient mechanical strength (hardness). The term "hardness" means that when an aqueous liquid is flowed

10 through a cylindrical column uniformly filled with the adsorbent, the pressure drop and the flow rate have a linear relationship up to at least 0.3 kgf/cm^2, as shown below in a reference example.

In the present invention, the material of the water-

15 insoluble porous carrier is not particularly limited. However, representative examples of the material include organic carriers comprising polysaccharides, such as cellulose, cellulose acetate, and dextrin; synthetic polymers such as polystyrene, styrene-divinylbenzene

20 copolymers, polyacrylamide, polyacrylic acid, polymethacrylic acid, polyacrylic acid esters, polymethacrylic acid esters, and polyvinyl alcohol. The water-insoluble porous carrier may have a coating layer comprising a polymer material having a hydroxyl group, such

25 as a polymer of hydroxyethyl methacrylate, a graft copolymer

such as a copolymer of a monomer having a polyethylene oxide
chain with another polymerizable monomer, or the like.
Among these materials, cellulose or a synthetic polymer such
as polyvinyl alcohol is preferably used for practical use
5   because active groups can easily be introduced into the
carrier surfaces.

Among these materials, the cellulose carrier is most
preferably used. The cellulose carrier has the advantages:
(1) It is hardly broken or causes fine particles because of
10   its relatively high mechanical strength and toughness, and
thus even if the body fluid is flowed through a column
filled with the cellulose carrier at a high flow rate,
consolidation little occurs to permit the body fluid to flow
at a high speed. (2) It has high safety as compared with a
15   synthetic polymer carrier. Therefore, the cellulose carrier
is most preferably used as the water-insoluble porous
carrier in the present invention.

As an anticoagulant for an extracorporeal circulation
therapy using an adsorber of the present invention, any one
20   of heparin, low-molecular weight heparin, nafamostat
mesilate, gabexate mesilate, argatroban, a sodium citrate
solution, and a citric acid-containing anticoagulant such as
an acid citrate-dextrose solution (ACD solution) and a
citrate-phosphate-dextrose solution (CPD solution) may be
25   used. In particular, from the viewpoint of whole blood

treatment, a citric acid-containing anticoagulant, heparin, low-molecular weight heparin, or nafamostat mesilate is particularly preferably used as the anticoagulant.

There are various methods for adsorbing the low-density
5   lipoproteins and fibrinogen from the body fluid using the adsorbent of the present invention. Representative examples of the methods include a method comprising taking out the body fluid and storing it in a bag or the like, mixing the adsorbent with the body fluid to remove the low-density
10   lipoproteins and fibrinogen, and then filtering off the adsorbent to obtain the body fluid free from the low-density lipoproteins and fibrinogen, and a method comprising preparing an adsorber comprising a container which is filled with the adsorbent and which has a body fluid inlet and
15   outlet, the outlet having a filter for passing the body fluid but not passing the adsorbent, and flowing the body fluid through the adsorber. Either of the methods may be used, but the latter method comprises a simple operation and can be incorporated into an extracorporeal circulation
20   circuit to permit the on-line efficient removal of the low-density lipoproteins and fibrinogen from the body fluid of a patient. Therefore, this method is most preferred as the method for adsorbing the low-density lipoproteins and fibrinogen using the adsorbent of the present invention.
25   The adsorber of the present invention comprises a

container which is filled with the adsorbent and which has a
body fluid inlet and outlet, the outlet having a filter for
passing the body fluid but not passing the adsorbent. The
capacity of the adsorber of the present invention must be

5   100 ml or more from the viewpoint of the effect of
decreasing the low-density lipoproteins and fibrinogen.
Although the capacity of the adsorber is not limited from
the viewpoint of adsorption ability, the capacity of the
adsorber is preferably 1000 ml or less, and more preferably

10   800 ml or less, because a blood pressure drop possibly
occurs when the amount of the blood taken out from the body
is excessively large. The capacity of the adsorber is most
preferably 400 ml or less from the viewpoint that even if
the adsorber is incorporated into the circuit of another

15   blood purification therapy such as hemodialysis or the like,
the amount of the blood extracorporeally circulated is not
excessively increased, and a blood pressure drop possibly
occurring when blood is taken out from the body can be
prevented as much as possible.

20   The adsorber of the present invention will be described
with reference to Fig. 1 which is a schematic cross-
sectional view of an example.

        In Fig. 1, reference numeral 1 denotes a fluid inlet,
reference numeral 2 denotes a fluid outlet, reference

25   numeral 3 denotes an adsorbent for low-density lipoproteins

and fibrinogen, reference numerals 4 and 5 each denote a

mesh, reference numeral 6 denotes a column, and reference

numeral 7 denotes an adsorber for low-density lipoproteins

and fibrinogen. However, the adsorber for low-density

5   lipoproteins and fibrinogen of the present invention is not

limited to this example, and the shape of the adsorber is

not particularly limited as long as it comprises a container

filled with the adsorbent for low-density lipoproteins and

fibrinogen, the container having a fluid inlet and outlet

10   and means for preventing an outflow of the adsorbent to the

outside.

Best Mode for Carrying Out the Invention

The present invention will be described in detail below

with reference to examples.

15   (REFERENCE EXAMPLE)

A glass cylindrical column (inner diameter: 9mm, column

length: 150 mm) comprising filters (pore size: 15 μm)

provided at both ends was uniformly filled with each of an

agarose material (Biogel A-5m produced by Bio-Rad

20   Laboratories, Inc., particle diameter: 50 to 100 mesh), a

vinyl polymer material (Toyopearl HW-65 produced by Tosoh

Corporation, particle diameter: 50 to 100 μm), and a

cellulose material (Cellulofine GC-700m produced by Chisso

Corporation, particle diameter: 45 to 105 μm). Then, water

25   was flowed through the column by a peristaltic pump to

determine the relation between the flow rate and pressure

drop ΔP. The results are shown in Fig. 2.

Fig. 2 shows that with Toyopearl HW-65 and Cellulofine

GC-700m, the flow rate increases substantially in proportion

5 to increases in pressure, while with BiogelA-5m, the flow

rate does not increase due to consolidation even when the

pressure is increased. In the present invention, like

Toyopearl HW-65 and Cellulofine GC-700m, a material showing

a linear relation between the pressure drop ΔP and the flow

10 rate up to 0.3 kgf/cm^2 is referred to as a "hard material".

(EXAMPLE 1)

First, 22 ml of water, 31 ml of a 4N NaOH aqueous

solution, and 32 ml of epichlorohydrin were added to 100 ml

of porous cellulose beads having an average particle

15 diameter of about 450 μm and a molecular weight exclusion

limit of 5×10^7 for globular proteins, followed by reaction at

40°C for 2 hours under stirring. After the reaction, the

beads were sufficiently washed with water to prepare

epoxidized cellulose beads. The amount of the epoxy groups

20 of the epoxidized cellulose beads was 16.4 μmol/ml (wet

volume).

On the other hand, 7.5 g of dextran sulfate (sulfur

content: about 18%, molecular weight: about 4000) was

dissolved in 25 ml of water to prepare an aqueous dextran

25 sulfate solution. Then, 50 ml of the epoxidized cellulose

beads wetted with water was added to the aqueous dextran
sulfate solution, and the resultant mixture was adjusted to
alkali with a NaOH aqueous solution, followed by reaction at
45°C for 1.5 hours. After the reaction, the beads were
5   sufficiently washed with water and brine, and a solution
prepared by dissolving 0.77 g of L-tryptophan in 50 ml of a
diluted NaOH aqueous solution was added to the beads,
followed by reaction at 50°C for 8 hours. Then, the beads
were sufficiently washed with water and brine to prepare
10 cellulose beads (A) with immobilized dextran sulfate and
tryptophan.

Beads A were charged in an acrylic column (volume 2.7
ml) having an inner diameter of 10 mm and a length of 34 mm
and comprising polyethylene terephthalate meshes provided at
15 both ends and each having an opening of 150 μm. Then, 40 ml
of the blood of a healthy adult, which was anticoagulated by
adding 5 units of heparin per milliliter of blood, was
circulated through the column at a flow rate of 6.5 ml/min
for 2 hours. Table 1 shows the numbers of the blood cells
20 in the pooled blood before and after the circulation for 2
hours. All blood cells showed excellent passing property.
Table 2 shows the concentrations of LDL-cholesterol,
fibrinogen, and HDL-cholesterol in the pooled blood before
and after the circulation. As shown in Table 2, LDL-
25 cholesterol is decreased from 116 mg/dl to 78 mg/dl, and

fibrinogen is decreased from 132 mg/dl to 93 mg/dl, but HDL-cholesterol is slightly decreased from 66 mg/dl to 62 mg/dl.

The amount of the immobilized tryptophan on beads A was determined from the nitrogen content of the adsorbent.

5   Namely, 1 ml of beads A was sufficiently washed with water, dried under reduced pressure at 60°C for 6 hours or more, and then quantitatively analyzed by a total nitrogen microanalyzer. As a result, the amount of the immobilized tryptophan on beads A was 7.8 μmol/ml.

10   The amount of the immobilized dextran sulfate of beads A was measured by utilizing the affinity of dextran sulfate for toluidine blue. Namely, about 100 ml of a toluidine blue (Basic blue 17 (Tokyo Kasei Kogyo Co., Ltd.) aqueous solution adjusted to about 90 mg/l was added to 3 ml of

15   beads A, and the resultant mixture was stirred for 10 minutes and allowed to stand. Then, the amount of the toluidine blue in the supernatant was determined by absorbance at 630 nm, and a decrease in amount of the toluidine blue was determined as the amount of the

20   immobilized dextran sulfate. As a result, the amount of the immobilized dextran on beads A was 0.16 μmol/ml, and the ratio TR/PA was 48.6.

(EXAMPLE 2)

First, 4 ml of water, 32 ml of a 4N NaOH aqueous

25   solution, and 29 ml of epichlorohydrin were added 100 ml of

the same cellulose beads as in EXAMPLE 1, followed by
reaction at 40°C for 2 hours under stirring. After the
reaction, the beads were sufficiently washed with water to
prepare epoxidized cellulose beads. The amount of the epoxy
5   groups of the epoxidized cellulose beads was 19.9 µmol/ml
(wet volume).

On the other hand, 7.5 g of the same dextran sulfate as
in EXAMPLE 1 was dissolved in 25 ml of water to prepare an
aqueous dextran sulfate solution. Then, 50 ml of the
10   epoxidized cellulose beads wetted with water was added to
the aqueous dextran sulfate solution, and the resultant
mixture was adjusted to alkali with a NaOH aqueous solution,
followed by reaction at 45°C for 3 hours. After the
reaction, the beads were sufficiently washed with water and
15   brine, and a solution prepared by dissolving 0.77 g of L-
tryptophan in 50 ml of a diluted NaOH aqueous solution was
added to the beads, followed by reaction at 55°C for 6 hours.
Then, the beads were sufficiently washed with water and
brine to prepare cellulose beads (B) with immobilized
20   dextran sulfate and tryptophan. The amount of the
immobilized tryptophan on beads B was 7.8 µmol/ml, the
amount of the immobilized dextran sulfate on beads B was
0.23 µmol/ml, and the TR/PA ratio was 33.8.

Beads B were charged in a column, and 40 ml of the
25   blood of a healthy adult was circulated through the column

for 2 hours by the same method as in EXAMPLE 1. Table 1

shows the numbers of the blood cells in the pooled blood

before and after the circulation. All blood cells showed

excellent passing property. Table 2 shows the

5 concentrations of LDL-cholesterol, fibrinogen, and HDL-

cholesterol in the pooled blood before and after the

circulation. As shown in Table 2, LDL-cholesterol is

decreased from 91 mg/dl to 51 mg/dl, and fibrinogen is

decreased from 220 mg/dl to 143 mg/dl, but HDL-cholesterol

10 is slightly decreased from 42 mg/dl to 41 mg/dl.

(EXAMPLE 3)

First, 55 ml of water, 15 ml of a 4N NaOH aqueous

solution, and 14 ml of epichlorohydrin were added 100 ml of

the same cellulose beads as in EXAMPLE 1, followed by

15 reaction at 40°C for 2 hours under stirring. After the

reaction, the beads were sufficiently washed with water to

prepare epoxidized cellulose beads. The amount of the epoxy

groups of the epoxidized cellulose beads was 8.8 µmol/ml

(wet volume).

20 On the other hand, 19.8 g of the same dextran sulfate

as in EXAMPLE 1 was dissolved in 25 ml of water to prepare

an aqueous dextran sulfate solution. Then, 50 ml of the

epoxidized cellulose beads wetted with water were added to

the aqueous dextran sulfate solution, and the resultant

25 mixture was adjusted to alkali with a NaOH aqueous solution,

followed by reaction at 45°C for 6 hours. After the reaction, the beads were sufficiently washed with water and brine, and a solution prepared by dissolving 0.77 g of L-tryptophan in 50 ml of a diluted NaOH aqueous solution was

5   added to the beads, followed by reaction at 50°C for 8 hours. Then, the beads were sufficiently washed with water and brine to prepare cellulose beads (C) with immobilized dextran sulfate and tryptophan. The amount of the immobilized tryptophan on beads C was 4.0 μmol/ml, the

10   amount of the immobilized dextran sulfate on beads C was 0.32 μmol/ml, and the TR/PA ratio was 12.5.

Beads C were charged in a column, and 40 ml of the blood of a healthy adult was circulated through the column for 2 hours by the same method as in EXAMPLE 1. Table 1

15   shows the numbers of the blood cells in the pooled blood before and after the circulation. All blood cells showed excellent passing property. Table 2 shows the concentrations of LDL-cholesterol, fibrinogen, and HDL-cholesterol in the pooled blood before and after the

20   circulation. As shown in Table 2, LDL-cholesterol is decreased from 163 mg/dl to 101 mg/dl, and fibrinogen is decreased from 215 mg/dl to 167 mg/dl, but HDL-cholesterol is slightly decreased from 60 mg/dl to 56 mg/dl.

(COMPARATIVE EXAMPLE 1)

25   Cellulose beads (D) with immobilized dextran sulfate

and tryptophan were prepared by the same method as in EXAMPLE 3 except that the reaction time of dextran sulfate was changed from 6 hours to 0.5 hour, and the amount of dextran sulfate was changed from 19.8 g to 7.5 g. The

5   amount of the immobilized tryptophan on beads D was 5.7 μmol/ml, the amount of the immobilized dextran sulfate on beads D was 0.08 μmol/ml, and the TR/PA ratio was 70.9.

Beads D were charged in a column, and 40 ml of the blood of a healthy adult was circulated through the column

10 for 2 hours by the same method as in EXAMPLE 1. Table 1 shows the numbers of the blood cells in the pooled blood before and after the circulation. Although erythrocytes showed excellent passing property, leukocytes and platelets are decreased to 66% and 63%, respectively, after the

15 circulation, and thus showed slightly low passing property. Table 2 shows the concentrations of LDL-cholesterol, fibrinogen, and HDL-cholesterol in the pooled blood before and after the circulation. As shown in Table 2, fibrinogen is decreased from 189 mg/dl to 127 mg/dl, but LDL-

20 cholesterol is slightly decreased from 86 mg/dl to 62 mg/dl, and HDL-cholesterol is slightly decreased from 66 mg/dl to 63 mg/dl.

(COMPARATIVE EXAMPLE 2)

First, 14 ml of water, 24 ml of a 4N NaOH aqueous

25 solution, and 29 ml of epichlorohydrin were added 100 ml of

the same cellulose beads as in EXAMPLE 1, followed by reaction at 40°C for 2 hours under stirring. After the reaction, the beads were sufficiently washed with water to prepare epoxidized cellulose beads. The amount of the epoxy groups of the epoxidized cellulose beads was 14.7 μmol/ml (wet volume).

Then, a solution prepared by dissolving 0.77 g of L-tryptophan in 50 ml of a diluted NaOH aqueous solution was added to 50 ml of the epoxidized cellulose beads, followed by reaction at 55°C for 6 hours. Then, the beads were sufficiently washed with water and brine to prepare cellulose beads (E) with immobilized tryptophan. The amount of the immobilized tryptophan on beads E was 8.2 μmol/ml.

Beads E were charged in a column, and 40 ml of the blood of a healthy adult was circulated through the column for 2 hours by the same method as in EXAMPLE 1. Table 1 shows the numbers of the blood cells in the pooled blood before and after the circulation. Although erythrocytes and leukocytes showed excellent passing property, platelets are decreased to 69% after the circulation and thus showed slightly low passing property. Table 2 shows the concentrations of LDL-cholesterol, fibrinogen, and HDL-cholesterol in the pooled blood before and after the circulation. As shown in Table 2, fibrinogen is decreased from 132 mg/dl to 77 mg/dl, but LDL-cholesterol is slightly

decreased from 116 mg/dl to 85 mg/dl, and HDL-cholesterol is

slightly decreased from 66 mg/dl to 61 mg/dl.

(EXAMPLE 4)

First, 42 ml of water, 100 ml of a 2N NaOH aqueous

5 solution, and 17 ml of epichlorohydrin were added 100 ml of

porous cellulose beads having an average particle diameter

of about 410 μm and a molecular weight exclusion limit of

5×10^7 for globular proteins, followed by reaction at 40°C for

2 hours. After the reaction, the beads were sufficiently

10 washed with water to prepare epoxidized cellulose beads.

The amount of the epoxy groups of the epoxidized cellulose

beads was 16.5 μmol/ml (wet volume).

On the other hand, 23.3 g of the same dextran sulfate

as in EXAMPLE 1 was dissolved in 39 ml of water to prepare

15 an aqueous dextran sulfate solution. Then, 50 ml of the

epoxidized cellulose beads wetted with water was added to

the aqueous dextran sulfate solution, and the resultant

mixture was adjusted to alkali with a NaOH aqueous solution,

followed by reaction at 45°C for 6 hours. After the

20 reaction, the beads were sufficiently washed with water and

brine, and a solution prepared by dissolving 0.93 g of L-

tryptophan in 50 ml of water by heating was added to the

beads. After the resultant mixture was adjusted to alkali

with a NaOH aqueous solution, reaction was performed at 50°C

25 for 8 hours. Then, the beads were sufficiently washed with

water and brine to prepare cellulose beads (F) with immobilized dextran sulfate and tryptophan. The amount of the immobilized tryptophan on beads F was 7.8 μmol/ml, the amount of the immobilized dextran sulfate on beads F was

5   0.17 μmol/ml, and the TR/PA ratio was 45.9.

Beads F were charged in an acrylic column (volume 3.5 ml) having an inner diameter of 10 mm and a length of 45 mm and comprising polyethylene terephthalate meshes provided at both ends and each having an opening of 50 μm. Then, 43 ml

10   of the blood of a healthy adult, which was anticoagulated by adding 5 units of heparin per milliliter of blood, was circulated through the column at a flow rate of 2.1 ml/min for 2 hours. Table 3 shows the numbers of the blood cells in the pooled blood before and after the circulation for 2

15   hours. All blood cells showed excellent passing property. Table 4 shows the concentrations of LDL-cholesterol, fibrinogen, and HDL-cholesterol in the pooled blood before and after the circulation. As shown in Table 4, LDL-cholesterol is decreased from 141 mg/dl to 94 mg/dl, and

20   fibrinogen is decreased from 234 mg/dl to 146 mg/dl, but HDL-cholesterol is slightly decreased from 49 mg/dl to 45 mg/dl.

(COMPARATIVE EXAMPLE 3)

First, 42 ml of water, 50 ml of a 2N NaOH aqueous

25   solution, and 17 ml of epichlorohydrin were added 100 ml of

the same cellulose beads as in EXAMPLE 4, followed by
reaction at 40°C for 2 hours under stirring. After the
reaction, the beads were sufficiently washed with water to
prepare epoxidized cellulose beads. The amount of the epoxy
5   groups of the epoxidized cellulose beads was 12.4 μmol/ml
(wet volume).

Then, 23.3 g of the same dextran sulfate in EXAMPLE 1
was dissolved in 39 ml of water to prepare an aqueous
dextran sulfate solution, and 50 ml of the epoxidized
10   cellulose beads wetted with water was added to the aqueous
dextran sulfate solution. After the resultant mixture was
adjusted to alkali with a NaOH aqueous solution, reaction
was performed at 45°C for 20 hours. Then, the beads were
sufficiently washed with water and brine to prepare
15   cellulose beads (G) with immobilized dextran sulfate. The
amount of the immobilized dextran sulfate on beads G was 0.6
μmol/ml.

Beads G were charged in a column, and 43 ml of the
blood of a healthy adult was circulated through the column
20   for 2 hours by the same method as in EXAMPLE 4. Table 3
shows the numbers of the blood cells in the pooled blood
before and after the circulation. Although erythrocytes
showed excellent passing property, leukocytes and platelets
are decreased to 66% and 63%, respectively, after the
25   circulation and thus showed slightly low passing property.

Table 4 shows the concentrations of LDL-cholesterol, fibrinogen, and HDL-cholesterol in the pooled blood before and after the circulation. As shown in Table 4, fibrinogen is decreased from 141 mg/dl to 89 mg/dl, but LDL-cholesterol

5   is slightly decreased from 234 mg/dl to 198 mg/dl, and HDL-cholesterol is slightly decreased from 49 mg/dl to 46 mg/dl.

(EXAMPLE 5)

First, 1.0 ml of cellulose beads (B) with immobilized dextran sulfate and tryptophan prepared in EXAMPLE 2 was

10   measured, and 10 ml of the plasma of a healthy person was added to the beads, followed by incubation at 37°C for 4 hours. After incubation, plasma was separated from the beads, and the concentrations of LDL-cholesterol, fibrinogen, albumin, IgG, and HDL-cholesterol of the plasma were

15   measured. The results are shown in Table 5. As shown in Table 5, LDL-cholesterol is decreased from 115 mg/dl to 81 mg/dl, and fibrinogen is decreased from 244 mg/dl to 186 mg/dl, but albumin is slightly decreased from 4.5 g/dl to 4.3 g/dl, IgG is slightly decreased from 1203 mg/dl to 1133

20   mg/dl, and HDL-cholesterol is slightly decreased from 62 mg/dl to 59 mg/dl.

(EXAMPLE 6)

First, 1.0 ml of cellulose beads (F) with immobilized dextran sulfate and tryptophan prepared in EXAMPLE 4 was

25   measured, and 10 ml of the plasma of a healthy adult was

added to the beads, followed by incubation at 37°C for 4

hours. After incubation, plasma was separated from the

beads, and the concentrations of LDL-cholesterol, fibrinogen,

albumin, IgG, and HDL-cholesterol of the plasma were

5   measured. The results are shown in Table 5. As shown in

Table 5, LDL-cholesterol is decreased from 87 mg/dl to 62

mg/dl, and fibrinogen is decreased from 260 mg/dl to 190

mg/dl, but albumin is slightly decreased from 4.7 g/dl to

4.5 g/dl, IgG is slightly decreased from 927 mg/dl to 876

10   mg/dl, and HDL-cholesterol is slightly decreased from 55

mg/dl to 54 mg/dl.

Table 1

	Adsorbent	Average particle diameter [μm]	Amount of immobilized dextran sulfate [μmol/ml]	Amount of immobilized tryptophan [μmol/ml]	TR/PA ratio [-]	Number of leukocytes [x10²/μl]			Number of platelets [x10⁴/μl]			Number of erythrocytes [x10⁴/μl]		
						Before blood perfusion	After blood perfusion	Ratio* [%]	Before blood perfusion	After blood perfusion	Ratio* [%]	Before blood perfusion	After blood perfusion	Ratio* [%]
Example 1	A	450	0.16	7.8	48.6	40	34	85	18.1	13.6	75	493	499	101
Example 2	B	450	0.23	7.8	33.8	55	48	87	16.8	12.4	74	504	510	101
Example 3	C	450	0.32	4.0	12.5	59	52	88	22.7	17.9	79	498	500	100
Comp. Example 1	D	450	0.08	5.7	70.9	47	31	66	19.0	12.0	63	441	444	101
Comp. Example 2	E	450	0	8.2	-	40	35	88	18.1	12.4	69	493	503	102

Ratio*: After blood perfusion/before blood perfusion × 100

Table 2

	Adsorbent	Average particle diameter [μm]	Amount of immobilized dextran sulfate [μmol/ml]	Amount of immobilized tryptophan [μmol/ml]	TR/PA ratio [-]	LDL-cholesterol [mg/dl]			Fibrinogen [mg/dl]			HDL-cholesterol [mg/dl]		
						Before *)	After *)	Rate of Decrease [%]	Before .*)	After *)	Rate of Decrease [%]	Before *)	After *)	Rate of decrease [%]
Example 1	A	450	0.16	7.8	48.6	116	78	33	132	93	30	66	62	6
Example 2	B	450	0.23	7.8	33.8	91	51	44	220	143	35	42	41	2
Example 3	C	450	0.32	4.0	12.5	163	101	38	215	167	22	60	56	7
Comp. Example 1	D	450	0.08	5.7	70.9	86	62	28	189	127	33	66	63	5
Comp. Example 2	E	450	0	8.2	-	116	85	27	132	77	42	66	61	8

Before: Before blood perfusion   After: After blood perfusion

Table 2 (continued)

	Amount of adsorption		
	LDL-cholesterol [mg/mL-gel]	Fibrinogen [mg/mL-gel]	HDL-cholesterol [mg/mL-gel]
Example 1	3.1	3.2	0.2
Example 2	3.2	6.2	0.1
Example 3	5.0	3.9	0.3
Comp. Example 1	2.0	5.3	0.3
Comp. Example 2	2.6	4.6	0.4

Table 3

Adsorbent	Average particle diameter [μm]	Amount of immobilized dextran sulfate [μmol/ml]	Amount of immobilized tryptophan [μmol/ml]	TR/PA ratio [-]	Number of leukocytes [×10²/μl]			Number of platelets [×10⁴/μl]			Number of erythrocytes [×10⁴/μl]		
					Before blood perfusion	After blood perfusion	Ratio* [%]	Before blood perfusion	After blood perfusion	Ratio* [%]	Before blood perfusion	After blood perfusion	Ratio* [%]
Example 4	F	410	0.17	7.8	45.9	59	52	88	22.7	17.9	79	498	500	100
Comp. Example 3	G	410	0.6	0	0	47	31	66	19.0	12.0	63	441	444	101

Ratio*: After blood perfusion/before blood perfusion × 100

Table 4

Adsorbent	Average particle diameter [μm]	Amount of immobilized dextran sulfate [μmol/ml]	Amount of immobilized tryptophan [μmol/ml]	TR/PA ratio [-]	LDL-cholesterol [mg/dl]			Fibrinogen [mg/dl]			HDL-cholesterol [mg/dl]		
					Before *)	After *)	Rate of Decrease [%]	Before *)	After *)	Rate of Decrease [%]	Before *)	After *)	Rate of decrease [%]
Example 4	F	410	0.17	7.8	45.9	141	94	33	234	146	38	49	45	8
Comp. Example 3	G	410	0.6	0	0	141	89	37	234	198	15	49	46	6

Before: Before blood perfusion   After: After blood perfusion

5

- 40 -

Table 4 (continued)

	Amount of adsorption		
	LDL-cholesterol [mg/mL-gel]	Fibrinogen [mg/mL-gel]	HDL-cholesterol [mg/mL-gel]
Example 4	3.2	5.9	0.3
Comp. Example 3	3.5	2.4	0.2

Table 5

Measurement items		LDL-cholesterol [mg/dl]			Fibrinogen [mg/dl]			Albumin [g/dl]		
Absorbent	Average particle diameter [μm]	Before adsorption	After adsorption	Rate of Decrease [%]	Before adsorption	After adsorption	Rate of Decrease [%]	Before adsorption	After adsorption	Rate of Decrease [%]
Example 5	B	450	115	81	30	244	186	24	4.5	4.3	4
Example 6	F	410	87	62	29	260	190	27	4.7	4.5	4

Table 5 (continued)

Measurement items	IgG [mg/dl]			HDL-cholesterol [mg/dl]		
	Before adsorption	After adsorption	Rate of Decrease [%]	Before adsorption	After adsorption	Rate of Decrease [%]
Example 5	1203	1133	6	62	59	5
Example 6	927	876	6	55	54	2

5

Brief Description of the Drawings

Fig. 1 is a schematic cross-sectional view showing an example of an adsorber of the present invention.

Reference numerals each denote the following:

5   1   body fluid inlet

2   body fluid outlet

3   adsorbent for low-density lipoproteins and fibrinogen

4, 5   mesh (means for preventing adsorbent outflow)

10   6   column

7   adsorber for low-density lipoproteins and fibrinogen

Fig. 2 is a graph showing the relation between the flow rate and pressure drop in the use of three types of gels.

15   Industrial Applicability

According to the present invention, low-density lipoproteins and fibrinogen can be efficiently adsorbed directly from a body fluid, particularly whole blood, to decrease the concentrations of these components in the body

20   fluid with minimizing losses of useful substances such as HDL and albumin. The present invention is particularly effective as a method for decreasing the concentrations of low-density lipoproteins and fibrinogen in the blood of a patient with arteriosclerosis, particularly arteriosclerosis

25   obliterans.